## SPECIFICATION CONTROL DRAWING

55A1883

EIGHT CONDUCTOR CABLE, SHIELDED, JACKETED, NORMAL WEIGHT, 600 VOLT

6-23-97

MODIFIED ETFE

This specification sheet forms a part of the latest issue of Raychem Specification 55A

SHIELD - NICKEL-COATED COPPER COMPONENT WIRES - 55A0813 JACKET - RADIATION-CROSSLINKED. FILAMENT BINDER AS REQUIRED

CABLE CONSTRUCTION DETAILS							
PART NUMBER	CONDUCTOR SIZE (AWG)	SHIELD SIZE (AWG)	JACKET THICKNESS (inch)		OUTSIDE DIAMETER (inch)		MAXIMUM WEIGHT (Ib/1000 ft)
			MINIMUM	NOMINAL	NOMINAL	MAXIMUM	
55A1883-26-*	26	38	.006	.008	.163	.186	24.3
55A1883-24-*	24	38	.006	.008	.179	.205	30.4
55A1883-22-*	22	38 -	.006	.008	.196	.224	38.9
55A1883-20-*	20	38	.007	.009	.224	.256	53.7
55A1883-18-*	18	38	.007	.009	.263	.301	77.1
55A1883-16-*	16	38	.007	.009	.285	.328	93.5
55A1883-14-*	14	36	.008	.010	.347	.398	142.

## CABLE RATINGS AND ADDITIONAL REQUIREMENTS

TEMPERATURE RATING: 200°C

Maximum continuous conductor temperature

VOLTAGE RATING: 600 volts (rms)

ACCELERATED AGING: 300 ± 3°C for 7 hours

BLOCKING: 200 ± 3°C for 6 hours

DIELECTRIC WITHSTAND: 1500 volts (rms), 60 Hz

FLAMMABILITY:

Procedure 1, 3 seconds (maximum); 3 in. (maximum);

no flaming of facial tissue

JACKET COLOR: White preferred

JACKET ELONGATION AND TENSILE STRENGTH:

Elongation, 50% (minimum)

Tensile Strength, 5000 lbf/in2 (minimum)

JACKET FLAWS:

Spark Test, 1000 volts (rms), 60 Hz, 100% test Impulse Dielectric Test, 6.0 kV (peak), 100% test LIFE CYCLE: 230 ± 3°C for 500 hours

LOW TEMPERATURE-COLD BEND: -65 ± 3°C for 4 hours

SHIELD COVERAGE: 85% (minimum)

VOLTAGE WITHSTAND TEST (POST ENVIRONMENTAL):

1000 volts (rms), 60 Hz, 1 minute

## PART NUMBER:

The "\*" in the part numbers shall be replaced by color code designators with a slash separating the component wire colors and a dash separating the component wire colors from the jacket color. Example: AWG 20, white, black, brown, red, orange,

> blue, yellow and gray component wires; white jacket: 55A1883-20-9/0/1/2/3/6/4/8-9

NOTE: Nominal values are for information only. Nominal values are not requirements.

COLORS AND COLOR CODE DESIGNATORS SHALL BE IN ACCORDANCE WITH MIL-STD-681

DIMENSIONS ARE IN INCHES, AND UNLESS OTHERWISE DESIGNATED ARE NOMINAL.

THIS SPECIFICATION SHEET TAKES PRECEDENCE OVER DOCUMENTS REFERENCED HEREIN. REFERENCED DOCUMENTS SHALL BE OF THE ISSUE IN EFFECT ON DATE OF INVITATION FOR BID.

Raychem

Raychem Corporation 300 Constitution Drive, Menlo Park, California 94025 1-800-2 Raychem Fax: 1-415-361-6297