

Side Weld Seals 3/8 in.





Mixed Unsortable Plastic Scrap

Mixed unsortable plastic scrap shall contain assorted plastics of multiple grades that are co-extruded, bonded or laminated together which are unsortable into individual grades Desco's bags are recyclable

Statshield[®] bags are packaged 100 per package in an oversized shielding bag. Shelf life of bags is minimum one year in normal indoor storage conditions.



STATFREE[®] ESD ULTRA CLEAR BAG



| Specifi | cati | on | s: |
|---------|------|----|----|
|---------|------|----|----|

| Electrical Properties | Typical Value | Test Procedures/Method |
|---------------------------------------------------------|------------------------------------------------------------|------------------------|
| Surface Resisitance: | 4 4044 4 | |
| (Interior and Exterior) Charge Generation: | < 1 x 10 ¹¹ ohms | Per ANSI/ESD STM11.11 |
| Teflon | -0.10 (nC/in ²) +0.10 (nC/in ²) | Modified Incline Plane |
| Quartz | +0.10 (nC/in ²) | Modified Incline Plane |
| Physical Properties: | | |
| Thickness | Nominal .0035" (.0889mm) ±10% | MIL-STD-3010, 1003 |
| Width (Inside Dimensions) Length (Inside Dimensions) | Nominal -0" / + .125" Nominal ± .125" | |
| Light Transmission | >90 (%) | STM D-1003 |
| Heat Seal | >8 (lbs/in) | 375°F, .75 sec 60 psi |
| Tensile Strength | >5,300 (MD/TD, psi) | ASTM D-882 |
| Puncture Res. | >25 lbs | MIL-STD-3010, 2065 |
| MVTR | 0.35 | ASTM F-1249 |

Chemical Properties

Polycarbonate compatible: Contains no Amines, Amides, or N-Octanoic Acid.

Bag is free of amines, N-octanoic acid, silicones and heavy metals.

ANSI/ESD S541 Section 6.1 Inside an EPA

"Packaging used within an EPA (that satisfies the minimum requirements of ANSI/ESD S20.20) shall be:

- Low charge generation
- · Dissipative or conductive materials for intimate contact

RoHS 2 and REACH Statement

None of the RoHS 2 restricted materials or REACH substances of very high concern as of 2012/12/19 are intentionally added in manufacturing this product. Ref: European Union Directive 2011/65/EU and Regulation (EC) No. 1907/2006/CE. See Desco Limited Warranty at Desco.com.

Meets ANSI/ESD S20.20 and Packaging standard ANSI/ESD S541 tested per ANSI/ESD STM11.11

Statshield® and Statfree® are Registered Trademarks of Desco Industries Inc.



DRAWING

NUMBER

13878

Specifications and procedures subject to change without notice.

STATFREE® ESD ULTRA CLEAR BAG, .0035" (.0889mm)

DESCO WEST: 3651 WALNUT AVE., CHINO, CA 91710 WEB SITE: Desco.com PHONE (909) 627-8178 DESCO EAST: ONE COLGATE WAY, CANTON, MA 02021-1407 PHONE (781) 821-8370

| DATE: | |
|-------|--|

July

2013