

UltraTEC[™] Series UT15,12,F2,4040 Thermoelectric Module



The UltraTEC[™] Series is a high heat pumping density thermoelectric module (TEM). The module is assembled with a large number of semiconductor couples to achieve a higher heat pumping capacity than standard single stage TEMs.

This product line is available in multiple configurations and is ideal for applications that require higher cooling capacities with limited surface area. Assembled with Bismuth Telluride semiconductor material and thermally conductive Aluminum Oxide ceramics, the UltraTEC[™] Series is designed for higher current and larger heat-pumping applications.

FEATURES **FEATURES**

- High heat pump density
- Precise temperature control
- Reliable solid state operation
- No sound or vibration
- DC operation
- RoHS compliant

APPLICATIONS

- Analytical instrumentation
- Clinical diagnostics
- Photonics laser systems
- Electronic enclosure cooling
- Food and beverage cooling
- Chillers (liquid cooling)

PERFORMANCE SPECIFICATIONS					
Hot side temperature (°C)	25	50			
Qmax (watts)	126.2	138.6			
Delta Tmax (°C)	67	75			
lmax (amps)	14.7	14.7			
Vmax (volts)	14.5	16.4			
Module resistance (ohms)	0.91	1.03			

SUFFIX	THICKNESS	FLATNESS & PARALLELISM	HOT FACE	COLD FACE	LEAD LENGTH
TA	0.112" +/- 0.001"	0.001"/0.001"	Lapped	Lapped	6.0″
ТВ	0.112" +/- 0.0005"	0.0005" / 0.0005"	Lapped	Lapped	6.0″

SEALING OPTION

SUFFIX	SEALANT	COLOR	TEMP RANGE	DESCRIPTION
RT	RTV	White	-60 to 204 °C	Non-corrosive, silicone adhesive sealant
EP	Ероху	Black	-55 to 150 °C	Low density syntactic foam epoxy encapsulant

Americas: +1 888.246.9050 Europe: +46.31.704.67.57 Asia: +86.755.2714.1166

clv.customerpos@lairdtech.com www.lairdtech.com



UltraTEC[™] Series UT15,12,F2,4040 Thermoelectric Module

PERFORMANCE CURVES



MECHANICAL DRAWING



Ceramic Material 96% Alumina Ceramics Solder Construction: 138°C BiSn

OPERATING TIPS

- Max operating temperature: 80°C
- Do not exceed Imax or Vmax when operating module
- Reference assembly guidelines for recommended installation

THR-DS-UT15,12,F2,4040 1013

Any information furnished by Laird Technologies, Inc. and its agents is believed to be accurate and reliable. All specifications are subject to change without notice. Responsibility for the use and application of Laird Technologies materials rests with the end user, since Laird Technologies and its agents cannot be aware of all potential uses. Laird Technologies makes no warranties as to the fitness, merchantability or suitability of any Laird Technologies materials or products for any specific or general uses. Laird Technologies shall note beliable for incidental or consequential damages of any kind. All Laird Technologies products are sold used to the start of the taird Technologies (Terms and Conditions of sale in effect from time to time, a copy of which will be furnished upon request. © Copyright 2009 Laird Technologies, Inc. If any fights Reserved. Laird, Laird Technologies, Inc. If any fights Reserved. Laird, Laird Technologies, Inc. If any set to the area or registered trade marks of Laird Technologies, Inc. If any set to the marks are trade marks or registered trade marks of Laird Technologies, Inc. If any set to the property of third parties. Nothing herein provides a license under any Laird Technologies or any third party intellectual property rights.